



# APEX MATERIAL INDUSTRIAL VIETNAM COMPANY LIMITED

LÔ A11, KHU CÔNG NGHIỆP KSB-KHU B, XÃ ĐẤT CUỐC, HUYỆN BẮC TÂN UYÊN, TỈNH BÌNH DƯƠNG

Tel: +84-274-3620911/3620777 Fax: +84-274-3620665

E-mail: sales@chu-shin.com Website: <https://en.vnapex.com/>

## Precipitated Calcium Carbonate

Property	B-201	A-101	A-201
Particle Size Distribution ( $\mu\text{m}$ )	0.6~1.2	0.8~1.5	1.0~2.5
Specific Surface Area ( $\text{cm}^2/\text{g}$ )	55,000	45,000	36,000
True specific gravity ( $\text{g}/\text{cm}^3$ )	2.6	2.6	2.6
Whiteness	96	96	96
Residue on 250 mesh	$\leq 0.1\%$	$\leq 0.1\%$	$\leq 0.1\%$
Oil absorption (DOTP, ml/100g)	55	45	35
Moisture	0.4%	0.3%	0.2%
Insoluble in HCl	$\leq 1.5\%$	$\leq 1.5\%$	$\leq 1.5\%$
Loss on ignition	43.5%	43.5%	43.5%
pH value	8~10	8~10	8~10
Assay of $\text{CaCO}_3$	99%	99%	99%

( The above data is a statistical average, provided for reference.)