



APEX MATERIAL INDUSTRIAL VIETNAM COMPANY LIMITED

LÔ A11, KHU CÔNG NGHIỆP KSB-KHU B, XÃ ĐẤT CUỐC, HUYỆN BẮC TÂN UYÊN, TỈNH BÌNH DƯƠNG

Tel: +84-274-3620911/3620777 Fax: +84-274-3620665

E-mail: sales@chu-shin.com Website: <https://en.vnapex.com/>

Ultra-fine Ground Calcium Carbonate

Property	CS-2200	CS-2000	CS-1800	AP-1600	AP-1500	AP-1200	AP-1000	AP-800	AP-700
Mean Particle Size d_{50} (μm)	1.32	1.68	2.0	2.5	3	4.5	6.5	10	13
Specific Surface Area (cm^2/g)	22400	20000	18000	16000	14000	12000	10000	8000	7000
Loose Bulk density (g/cm^3)	0.27	0.31	0.34	0.36	0.40	0.45	0.5	0.6	0.65
Particle passing point d_{100} (μm)	< 11	< 16	< 23	< 30	< 33	< 68	< 120	< 125	< 125
Whiteness	100	100	100	100	100	99	99	99	99
Oil absorption (DOTP, ml/100g)	41	37	35	34	32	28	29	32	31
Moisture	$\leq 0.50\%$								
Insoluble in HCl	$\leq 1.5\%$								
pH value	8~10								
Assay of CaCO_3	99%								

(The above data is a statistical average, provided for reference.)