



APEX MATERIAL INDUSTRIAL

No.1, Aly. 3, Ln. 67, Sec. 6, Zhonghua Rd., Hsinchu City 300, Taiwan
LÔ A11,KHU CÔNG NGHIỆP KSB-KHU B,XÃ ĐẤT CUỐC ,HUYỆN BẮC TÂN UYÊN,TỈNH BÌNH DƯƠNG

Tel: +84-274-3620911/3620777 TEL : +886-3-5372126

E-mail: sales@chu-shin.com Website: <https://www.chu-shin.com/en/>

Calcium Carbonate Masterbatch

Property	Testing Methods	LL-103	LL-105	LD-113	PP-103
Calcium Carbonate Content (%)	--	80~85	80~85	80~85	80~85
Average Particle Size of Calcium Carbonate(μm)	Malvern	2.0	2.0	2.0	3.0
Melt Flow 190°C,2.16kg (g/10min)	ASTM D1238	<1	<1	<1	--
Melt Flow 230°C,2.16kg (g/10min)	ASTM D1238	--	--	--	<2
Density (g/cm ³)	ASTM D1505	1.9~2.1	1.9~2.1	1.9~2.1	1.9~2.1
Moisture (%)	ASTM D644	<0.25	<0.25	<0.25	<0.25
Carrier	--	PE	PE	PE	PP
Application	--	Trash bags, Cleaning bags			Woven bags, packaging bags

(The above data is provided as an average reference for testing purposes)