



APEX MATERIAL INDUSTRIAL VIETNAM COMPANY LIMITED

LÔ A11, KHU CÔNG NGHIỆP KSB-KHU B, XÃ ĐẤT CUỐC, HUYỆN BẮC TÂN UYÊN, TỈNH BÌNH DƯƠNG

Tel: +84-274-3620911/3620777 Fax: +84-274-3620665 Website: <https://www.vnapex.com/>

PVC Compound

Property	Application	Gravity (g/cm ³)	Hardness	Tensile Strength (Kgf/mm ²)	Elongation %
GPC35PYBK23	Optic Fiber Cable	1.55	96A	1.60	200
GPC0PYBK18	Square Pipe	1.67	72D	--	--
GPC0PYBK22	Rigid PVC Profiles	1.64	72D	--	--
GPC0PNYE01	Rigid Plastic Profiles	1.49	69D	--	--
GPC0PYGY12	Valve	1.38	71D	--	--
GPC0PYWT05*	Pipe PVC	1.37	70D	--	--
GPC50PYCR01	Transparent PVC	1.25	80A	--	--
GPC50PYCR02*	Transparent Injection material	1.23	81A	--	--
GPC60PYBK25*	Motorcycle Handlebar	1.32	68A	--	--

(The above data is provided as an average reference for testing purposes)