



## APEX MATERIAL INDUSTRIAL VIETNAM COMPANY LIMITED

LÔ A11, KHU CÔNG NGHIỆP KSB-KHU B, XÃ ĐẤT CUỐC, HUYỆN BẮC TÂN UYÊN, TỈNH BÌNH DƯƠNG

Tel: +84-274-3620911/3620777 Fax: +84-274-3620665

E-mail: sales@chu-shin.com Website: <https://en.vnapex.com/>

# Ultra-fine Talc Powder

Property	325H	325HA	1250H	2000B	2000A	3000B	3000A
Mean particle size (µm)	9.0	8.5	6.0	5.0	5.0	4.0	4.0
Surface area (cm <sup>2</sup> /g)	5500	5500	6500	7500	7500	8500	8500
Residue on 250 mesh	≤ 0.3%	≤ 0.3%	≤ 0.1%	≤ 0.05%	≤ 0.05%	≤ 0.05%	≤ 0.05%
Loose Bulk density (g/cm <sup>3</sup> )	0.36	0.34	0.25	0.20	0.20	0.16	0.16
Whiteness	92	96	92	92	96	92	96
Moisture	0.2%	0.4%	0.3%	0.4%	0.4%	0.4%	0.4%
Loss on ignition	26±6	18±5	26±6	6.5±3	5.5±3	6.5±3	5.5±3
SiO <sub>2</sub>	54%	63%	54%	62%	63%	62%	63%
MgO	25%	32%	25%	31%	32%	31%	32%
pH value	8.5±1	8.5±1	8.5±1	8.5±1	8.5±1	8.5±1	8.5±1

( The above data is a statistical average, provided for reference.)